



Wood Finishing Products
A Division of Farwest Paint Mfg. Co.

SPECIFICATION SHEET

Daly's Wood Stain

Product:10000

3/2016

DESCRIPTION:

Daly's **Wood Stain** is a penetrating, fade resisting pigmented stain, that produces the beauty of a hand-rubbed tung oil finish.

RECOMMENDED USES:

INTERIOR USE: For all interior wood surfaces such as furniture, paneling, cabinets, doors and floors.

EXTERIOR USE: May be used on exterior surfaces such as doors, patio furniture and boats. Finish with a Daly's clear product suitable to your need.

RECOMMENDED SYSTEMS:

Stir well before and while using. Surface must be dry, clean and smooth. Where oil rubbed finish is not desired, apply stain and wipe to desired tone. Allow 12 to 24 hours to dry. When using whites and heavily pigmented stains allow to dry 24 hours or longer.

OIL RUBBED FINISH:

1. Sand surface with 120 paper, remove sanding dust.
2. Apply a liberal coat, allow 5 minutes penetration.
3. While still wet with stain, sand with 400 grit sandpaper until smooth, wipe with absorbent rag for desired tone.

FINAL FINISH: For greater protection and beauty, apply one of Daly's finishes for desired effect.

NOTES:

To avoid spottiness on soft wood, such as pine, fir and hemlock, Daly's BENITE™ is recommended as a pre-stain conditioner or use Daly's **Wood Stain** Clear Base. When filling is required, use a paste wood filler. When finishing and using one of Daly's other products, follow directions on container prior to application.

COLORS & TINTING:

Comes in Daly's standard colors that can be intermixed for additional colors. If tinting is required, up to 6 ounces per gallon of universal machine colorants or ground oils may be added. To lessen the intensity of color use Daly's **Wood Stain** Clear Base. Always test first for compatibility and desired effect.

THINNING: Do not thin.

CLEAN UP: Paint thinner (Mineral spirits).

SURFACE PREPARATION:

All surfaces to be finished must be free of loose dirt, dust, other contaminants, and must be dry.

APPLICATION: Brush, rag, foam brush or spray.

COVERAGE: Approximately 400 to 600 sq.ft. per gallon depending on surface texture and dryness.

DRY TIME:

Temperature, humidity and ventilation will affect dry time.

At 77°F, with 50% Relative Humidity:

WOOD TONE COLORS: 2 to 4 hours to touch, 12 to 24 hours to recoat

WHITES AND OFF-WHITES: 4 to 6 hours to touch, 24 hours or longer to recoat

CAUTIONS:

CONTAINS PETROLEUM DISTILLATE: VAPOR HARMFUL. MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

PRECAUTIONS: Keep away from heat and flame. Prevent build-up of vapors by opening windows and doors to achieve cross ventilation.

USE ONLY WITH ADEQUATE VENTILATION. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness, or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Close container after each use.

First Aid: If swallowed, do not induce vomiting. Call physician immediately. If you experience difficulty breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water.

SPECIAL INSTRUCTIONS:

IF SPILLED: Contain spilled materials and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

DISPOSAL OF OILY RAGS: To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed, metal container.

VEHICLE TYPE: Tung Oil, Modified Resin, Pigments.

WEIGHT PER GALLON: 6.9 to 7.6 pounds per gallon

% SOLIDS: 30 to 32% by volume, 34 to 43% by weight

FLASH: 107°F Seta Flash Closed Cup

V.O.C.: Maximum 550 grams per liter.

FLASH: 15 seconds #2 Zahn Cup.

Daly's Wood Finishing Products

4522 S 133rd St, Tukwila, WA 98168

www.dalyswoodfinishes.com

phone(206) 244-8844

toll free(800) 727-9694

fax(206) 246-7691