



Wood Finishing Products

Paste Wood Filler

Product: 14310

08/06/03

SPECIFICATION SHEET

DESCRIPTION:	Daly's Paste Wood Filler packs the pores of open grain woods such as mahogany, oak, walnut and others when a smoother finish is desired. Filler prevents finish coat from "falling" into pore structure. Daly's Paste Wood Filler is compatible with most finishing top coats, however check label and test prior to application.
RECOMMENDED USES:	Furniture, cabinet work, wood paneling, doors, floors, or wherever open grained woods are to be filled - interior or exterior, including marine surfaces.
RECOMMENDED SYSTEMS:	Simply fill bare wood, stain if desired, then apply final finish coats. (Note: Stain after filler has dried, as opposed to staining before filler has been applied. Resulting stain color will be clearer than when staining prior to filling.) When staining or using on dark woods, tint filler to desired shade by thinning with stain color (solvent base) or use universal machine colorants.
APPLICATIONS:	Thin Paste Wood Filler approximately 25-30% with paint thinner. Apply with short bristle brush, working cross grain (on woods with large pore structure apply first with the grain, then across grain.) Allow about 15 minutes drying time, or until dull. Work filler into grain by wiping first in a circular motion, then with the grain, using a coarse rag or burlap to remove all excess filler. Wipe immediately after removing excess filler with a soft, absorbent rag until the surface is clear and free of all cloudiness. Allow to dry 8 to 24 hours, depending upon conditions before application of finish coats. FLOORS: The same procedure is used in filling floors. However, it is important filler should not be applied over too large of an area at one time, as all excess filler must be removed while still moist.
THINNING:	Thin filler approximately 25-30% with paint thinner.
CLEAN UP:	Paint thinner (Mineral spirits).
SURFACE PREPARATION:	All surfaces to be finished must be free of loose dirt, dust, other contaminants and must be dry.
COVERAGE:	600 sq.ft. per gallon after thinning.
DRY TIME:	8 to 24 hours.
MAINTENANCE:	Not applicable.
CAUTIONS:	CONTAINS PETROLEUM DISTILLATE: VAPOR HARMFUL. MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION. Notice: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. PRECAUTIONS: Keep away from heat and flame. Prevent build-up of vapors by opening windows and doors to achieve cross ventilation.

CAUTIONS(cont'd): **USE ONLY WITH ADEQUATE VENTILATION.** Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate properly fitted respirator (NIOSH/MSHA approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.

First Aid: If swallowed, do not induce vomiting. Call physician immediately. If you experience difficulty in breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water.

SPECIAL INSTRUCTIONS: **If spilled,** contain spilled materials and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

Disposal of oily rags: To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed, metal container.

KEEP OUT OF REACH OF CHILDREN

VEHICLE TYPE: Drying oil.

WEIGHT PER GAL: Approximately 13.8 lb.

% SOLIDS: 78% - by volume.

FLASH: 107°F Seta Flash Closed Cup

V.O.C.: After thinning, maximum 320 grams per liter.

VISCOSITY: N/A.

Daly's Wood Finishing Products

3525 Stone Way N, Seattle, WA 98103

phone(206) 633-4200

toll free(800) 735-7019

fax(206)632-2565