



SPECIFICATION SHEET

Seafin Ship`N Shore™

Product:15100

Waterproofing Sealer

11/2016

DESCRIPTION:

Daly's **SeaFin Ship `N Shore** is a deeply penetrating wood waterproofing sealer. As it penetrates, **SeaFin Ship `N Shore** becomes an integral part of the cell structure, hardening the wood from 15% to 25%. **SeaFin Ship `N Shore** is practically colorless, odorless and non-toxic. Does not raise the grain and because of deep penetration, leaves no surface film to chip, crack, chalk, blister or peel. **SeaFin Ship `N Shore** is an excellent conditioner for wood surfaces such as decks, handrails, cabins, hulls, masts and canvas or any area where paint or varnish is to be used.

RECOMMENDED USES:

SeaFin Ship `N Shore is fully compatible with urethane varnishes and practically all stain products. It will give added life to weather worn exterior stained surfaces, and applied to metals aids in preventing rust. **SeaFin Ship `N Shore** is recommended for added protection on non-painted surfaces such as decks, docks and siding having a western or southern exposure or where salt water spray is a problem, and also for cedar paneling in bathrooms and high humidity areas where no surface finish is desired. Use on benches and railings to protect against wear and tear.

RECOMMENDED SYSTEMS:

SeaFin Ship `N Shore may be brushed, sprayed or dipped. Apply a full, flowing coat. Allow 24 hours drying time. When used under extremely damp conditions, allow 36-48 hours drying time. For added protection on a non-painted surface, such as a dock or patio, apply a second coat of **SeaFin Ship `N Shore** after 24 hours drying time. The application of this second coat will give years of added protection.

COLORS & TINTING: If tinting is desired, use colors in oil.

THINNING: Do not thin. Product is ready to use as packaged.

CLEAN UP: Paint thinner (Mineral spirits).

SURFACE PREPARATION:

All surfaces to be finished must be free of loose dirt, dust, other contaminants and must be dry.

APPLICATION: Brush, roller, spray or dipping.

COVERAGE:

200 to 300 sq.ft. per gallon for the first coat, depending on surface texture. 400-500 sq.ft. per gallon for the second coat.

DRY TIME:

Temperature, humidity and ventilation can affect drying time. 2 to 6 hours dry to touch. 24-48 hours dry to re-coat depending on weather conditions.

MAINTENANCE:

When dulling or drying out occurs, another coat of **SeaFin Ship `N Shore** will restore the surface.

CAUTIONS:

CONTAINS PETROLEUM DISTILLATE: VAPOR HARMFUL. MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION.

Notice: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

PRECAUTIONS: Keep away from heat and flame. Prevent build-up of vapors by opening windows and doors to achieve cross ventilation.

USE ONLY WITH ADEQUATE VENTILATION. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.

First Aid: If swallowed, do not induce vomiting. Call physician immediately. If you experience difficulty in breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water.

KEEP OUT OF REACH OF CHILDREN

Warning: Rags and other waste materials soiled with this product may spontaneously catch fire if improperly discarded. Soak soiled rags and waste immediately after use in a water-filled, closed metal container. For disposal guidance of unused materials, contact a house hold hazardous waste program or your local or state government environmental control agency.

SPECIAL INSTRUCTIONS:

IF SPILLED: Contain spilled materials and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

DISPOSAL OF OILY RAGS: To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed, metal container.

STORAGE:

SeaFin Ship `N Shore will remain in good condition in the original unopened container for a period of years. Once opened **SeaFin Ship `N Shore** should not be stored in a partially full container. Pour unused product into smaller containers or add clean marbles into the opened container to raise the liquid level and eliminate air.

VEHICLE TYPE: Resins, Rosin and Oil Modified Urethane

WEIGHT PER GALLON: 6.9 pounds per gallon.

% SOLIDS: 23% by volume.

FLASH: 104°F

V.O.C.:Maximum 600 grams per liter.

Daly's Wood Finishing Products

4522 S 133rd St, Tukwila, WA 98168

www.dalyswoodfinishes.com

phone(206) 244-8844

toll free(800) 727-9694

fax(206) 246-7691