



Wood Finishing Products

SeaFin™ Teak Oil

Natural

Product: 15000

08/13/03

SPECIFICATION SHEET

DESCRIPTION: Daly's **SeaFin Teak Oil** is a penetrating, hard-drying, low sheen oil finish, designed for sealing and finishing interior and exterior woods, especially teak on boats. It will not chip, crack, peel or blister when properly applied and maintained, thus reducing maintenance by eliminating scraping, sanding and refinishing. **SeaFin Teak Oil** may be applied while vessel is underway to refurbish or touch up worn or marred areas, and may be used as a maintenance and intermittent coat, giving existing varnished surfaces longer life. When used on teak or wood decks, **SeaFin Teak Oil** provides a durable non-slip surface to repel water and resist wear.

RECOMMENDED USES: MARINE AND EXTERIOR USE: Teak and wood decks, hatch covers, bright work, mahogany, finishing hardwood rails, doors, polishing varnished surfaces, refurbishing or touching up worn or marred areas, and as a maintenance and intermittent coat for longer life of existing varnished surfaces.
INTERIOR USE: A low sheen finish for stained or natural surfaces; kitchen and bathroom cabinets and other woodwork exposed to moisture.

RECOMMENDED SYSTEMS: For Interior and Exterior Work:

1. Apply to clean, dry surface with cloth, brush or roller.
2. Allow 5 to 15 minutes penetration.
3. While surface is wet, sand until smooth with 400A wet/dry sandpaper.
4. Wipe dry with a clean cloth.
5. Allow 8 to 12 hours drying time.
6. Apply a second coat, repeating above procedure.

For interior surfaces, 3 - 4 coats are recommended.
For exterior surfaces, approximately 6 or more coats are recommended.
NOTE: On open grain woods like oak, watch for "bleed back". Should this occur, continue to wipe every 15-20 minutes until beads no longer appear, or allow to dry and then rub out with a fine wood finishing pad before applying another coat.
Over Stained Surfaces:

1. Be SURE the stain is fully dry - 24 to 48 hours. TEST FIRST! Should an application of **SeaFin Teak Oil** cause the stain color to run, allow further drying time.
2. Apply a thin, even coat by brush, spray or rag.
3. Allow to set for 5 to 15 minutes, then gently wipe to a "damp-dry" look.
4. One to three coats is adequate in most cases, but must be dictated by sample applications to achieve desired finished appearance.

NOTE: DO NOT WETSAND CLEAR COATS, AS THIS WILL DAMAGE THE STAIN.

THINNING: Do not thin.

CLEAN UP: Paint thinner (Mineral spirits).

SURFACE PREPARATION: All surfaces to be finished must be free of loose dirt, dust, other contaminants and must be dry.

APPLICATION: Brush, roller or spray, wiping or brushing as desired.

COVERAGE: 200 to 400 sq.ft. per gallon depending on surface texture.

DRY TIME: 4 to 6 hours to touch. Overnight to recoat or use. **DAMP WEATHER:** If humidity is high and conditions are moist, allow 24 to 36 hours between applications.

MAINTENANCE: To renew existing oiled or varnished surfaces, clean first, then dampen cloth with **SeaFin Teak Oil**, wipe on and polish dry.

CAUTIONS: **CONTAINS PETROLEUM DISTILLATE: VAPOR HARMFUL. MAY AFFECT THE BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN, NOSE AND THROAT IRRITATION.**
Notice: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

PRECAUTIONS: Keep away from heat and flame. Prevent build-up of vapors by opening windows and doors to achieve cross ventilation.

USE ONLY WITH ADEQUATE VENTILATION. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate properly fitted respirator(NIOSH/MSHA approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.

First Aid: If swallowed, do not induce vomiting. Call physician immediately. If you experience difficulty in breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water.

If spilled, contain spilled materials and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

KEEP OUT OF REACH OF CHILDREN

SPECIAL INSTRUCTIONS: **DISPOSAL OF OILY RAGS:** To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed container.

VEHICLE TYPE: Tung, Phenolic, Oil Modified Urethane

WEIGHT PER GAL: 7 lb.

% SOLIDS: 30% - volume

35% - weight

FLASH: 107°F Seta Flash Closed Cup

V.O.C.: Maximum 550 grams per liter

VISCOSITY: 15 Seconds #2 Zahn Cup

Daly's Wood Finishing Products

3525 Stone Way N, Seattle, WA 98103

phone(206) 633-4200

toll free(800) 735-7019

fax(206)632-2565